

LUBRICANTS

AKLUB K 17

TBF 12-024-04

AKLUB K 17 Has both internal and external lubricating properties and maintains compatibility with PVC.

It is non-toxic, can therefore be used in opaque food packaging formulations.

Definition

Esther wax

Chemical - Physical Properties

Form	Flakes
Color	Yellowish white
Acid value	4,0 max.
Melting point	59,0 - 60,0 °C
Bulk density(g/l)	500,0 ± 10,0

Application

Rigid PVC processes

Recommended Charges

Depending on formulation and processing conditions; 0,2 - 0,5 phr.

Standard Packaging

20 - 25 kg. net. PE/PP bags

A material safety data sheet for the safe handling of this product is available on request

The information in this catalogue is based on our own knowledge and personal experience. It should therefore only be regarded as a guide and not be taken as any form of guarantee whatsoever. In the event of specific queries, kindly contact our technical service.