

## LUBRICANTS

### AKLUB K 90

TBF 12-019-02 / Rev.02

Aklub K-90 has both mould releasing and external lubricant properties.

It gives shine to colorless and non-polar products.

It is also used in rigid plasticized PVC processes.

Since AKLUB K-90 is nontoxic, it can also be used in food packaging industry.

#### Definition

Oxidized polyethylene wax.

#### Chemical - Physical Properties

Form	Powder
Color	White
Acid value	15,0-18,0.
Melting point	100-110 °C

#### Application

Rijid PVC processes  
Plasticized PVC processes

#### Recommended Charges

Depending on formulation and processing conditions; 0,2 - 0,5 phr.

#### Standard Packaging

20 - 25 kg. net. PE/PP bags

A material safety data sheet for the safe handling of this product is available on request

The information in this catalogue is based on our own knowledge and personal experience. It should therefore only be regarded as a guide and not be taken as any form of guarantee whatsoever. In the event of specific queries, kindly contact our technical service.